



POLY FERT
— FOR INDUSTRY & TRADE —

Egyptian Kaolin

Chemical Analysis Of *Kalabsha* Kaolin

Elements	%
SiO ₂	45.45
Al ₂ O ₃	36.35
TiO ₂	3.04
Fe ₂ O ₃	0.64
MgO	0.01
CaO	0.17
Na ₂ O	0.04
K ₂ O	0.01
P ₂ O ₅	0.09
SO ₃	0.06
Cl	0.06
L.O.I	14.08



Address :

24 Misr Lel Taamir Buildings / Mustafa El Nahhas Extension Fourth floor, Apartment 20 Above EL Ezaby Pharmacy

Phone :

02-235-735-55
info@poly-fert.com



POLY FERT
— FOR INDUSTRY & TRADE —