



POLY FERT
— FOR INDUSTRY & TRADE —

MINE GYPSUM SPECIFICATION

Chemical analysis:

| Constituents | High Grade | Low Grade |
|---|------------|------------|
| Combined water | 19.50 min. | 18.90 min. |
| CaSO ₄ 2H ₂ O | 93.00 min. | 90.40 min. |
| CaO | 30.5 : 33 | 30.5 : 33 |
| SO ₃ | 43.5 : 46 | 43.5 : 46 |
| MgO | 0.10 max. | 0.10 max. |
| SiO ₂ + IR | 1.00 max. | 1.50 max. |
| Al ₂ O ₃ + Fe ₂ O ₃ | 0.25 max. | 0.25 max. |
| Cl | 0.008 max. | 0.01 max. |
| Whiteness | 95% min. | 95% min. |

Size: Run of mine or crushed 0 to 40 cm max.

or crushed according to customer requirements

Address :

24 Misr Lel Taamir Buildings / Mustafa El Nahhas Extension Fourth floor, Apartment 20 Above EL Ezaby Pharmacy

Phone :

02-235-735-55
info@poly-fert.com



POLY FERT
— FOR INDUSTRY & TRADE —