



POLY FERT
— FOR INDUSTRY & TRADE —

QUARTZ SPECIFICATION

Chemical Analysis

ELEMENT	RESULT%
SiO ₂	99.0 - 99.7
TiO ₂	0.01 (max.)
Al ₂ O ₃	0.01 - 0.2
Fe ₂ O ₃	0.0 - 0.1
MnO	0.0 - 0.01
MgO	0.05 (max.)
CaO	0.1 - 0.7
Na ₂ O	0.01 - 0.06
K ₂ O	0.05 (max.)
P ₂ O ₅	<0.01
L.O.I	0.12 - 0.35

Size: Run of mine or crushed from 1 to 15 cm max.

And/or: According to customer requirements.



Lumps



Address :

24 Misr Lel Taamir Buildings / Mustafa El Nahhas Extension Fourth floor, Apartment 20 Above EL Ezaby Pharmacy

Phone :

02-235-735-55
info@poly-fert.com



POLY FERT
— FOR INDUSTRY & TRADE —