



POLY FERT
— FOR INDUSTRY & TRADE —

MINE GYPSUM SPECIFICATION

Chemical analysis:

Constituents	High Grade	Low Grade
Combined water	19.50 min.	18.90 min.
CaSO ₄ 2H ₂ O	93.00 min.	90.40 min.
CaO	30.5 : 33	30.5 : 33
SO ₃	43.5 : 46	43.5 : 46
MgO	0.10 max.	0.10 max.
SiO ₂ + IR	1.00 max.	1.50 max.
Al ₂ O ₃ + Fe ₂ O ₃	0.25 max.	0.25 max.
Cl	0.008 max.	0.01 max.
Whiteness	95% min.	95% min.

Size: Run of mine or crushed 0 to 40 cm max.

or crushed according to customer requirements

Address :

24 Misr Lel Taamir Buildings / Mustafa El Nahhas Extension Fourth floor, Apartment 20 Above EL Ezaby Pharmacy

Phone :

02-235-735-55
info@poly-fert.com



POLY FERT
— FOR INDUSTRY & TRADE —